

SABIC® PP 612MK46

PP block copolymer for Injection moulding

Description:

This grade is especially developed for pails and containers. Special characteristics of this grade are a high crystallisation temperature, very high flow in combination with medium impact performance and neutral taste & odor performance. This enables outstanding processability, very easy mould filling and short cycle times. SABIC® PP 612MK46 is formulated with a combined processing and antistatic additive package. It is also available in a general purpose additive package.


Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

Typical values

Revision 20090604

Properties	Unit (SI)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg	g/10 min	33	ISO 1133
Density	kg/m ³	905	ISO 1183
Mechanical properties			
Tensile test			ISO 527
stress at yield	MPa	27	
stress at break	MPa	18	
strain at break	%	200	
Flexural test			ASTM D 790
Flexural modulus	MPa	1450	
Izod impact notched			ISO 180/4A
at 23 °C	kJ/m ²	8.0	
at 0 °C	kJ/m ²	5.0	
at -20 °C	kJ/m ²	4.0	
Charpy impact notched			ISO 179
at 23 °C	kJ/m ²	9.0	
at 0 °C	kJ/m ²	5.5	
at -20 °C	kJ/m ²	4.0	
Hardness Shore D	-	67	ISO 868
Thermal properties			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	°C	55	ISO 75/A
at 0.45 MPa (HDT/B)	°C	102	ISO 75/B
Vicat softening temperature			
at 10 N (VST/A)	°C	147	ISO 306/A
at 50 N (VST/B)	°C	70	ISO 306/B



SABIC® PP 612MK46

PP block copolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.